



510 Gilmore Ave., Suite C  
 Stockton, CA 95203  
 Toll-free: 800-590-PLAS  
 Phone: 209-464-2701  
 Fax: 209-464-5760

### MATERIAL WEIGHT - lbs. per square foot

MATERIAL		THICKNESS IN INCHES																						
		.375	.500	.625	.750	.875	1.000	1.125	1.250	1.500	1.750	2.000	2.250	2.500	2.750	3.000	3.250	3.500	3.750	4.000	4.250	4.500	4.750	5.000
ACETAL / DELRIN®	Nat, Blk	2.78	3.70	4.63	5.56	6.49	7.41	8.34	9.27	11.10	13.00	14.80	16.70	18.50	20.40	22.20	24.10	26.00	27.80	29.70	31.55	33.40	35.26	37.00
	570*	-	4.06	5.07	6.09	7.10	8.12	9.14	10.10	12.20	-	-	-	-	-	-	-	-	-	-	-	-	-	-
	AF Blend	3.00	4.01	5.01	6.01	7.01	8.01	9.01	10.00	12.00	14.00	16.00	-	-	-	-	-	-	-	-	-	-	-	-
	SD	2.62	3.48	4.36	5.23	6.10	6.97	7.84	8.72	10.50	12.20	13.90	-	-	-	-	-	-	-	-	-	-	-	-
HALAR® 902	Natural	3.33	4.45	5.55	6.66	7.78	8.89	10.00	11.14	13.34	15.55	17.76	19.97	22.27	24.48	26.69	28.90	31.10	33.31	35.52	-	-	-	-
NYLON	Nat, Blk Trogamid	2.22	2.97	3.71	4.45	5.19	5.93	6.67	7.41	8.90	10.40	11.90	13.30	14.80	16.30	17.80	19.30	20.80	22.20	23.70	-	-	-	-
	MD	2.22	2.97	3.71	4.45	5.19	5.93	6.67	7.41	8.90	10.40	-	-	-	-	-	-	-	-	-	-	-	-	-
PBT	Natural	2.67	3.56	4.45	5.35	6.24	7.13	8.02	8.91	10.70	12.50	14.30	16.00	17.80	19.60	21.40	23.20	25.00	26.70	28.50	-	-	-	-
PEEK™	Natural	2.54	3.38	4.23	5.07	5.92	6.76	7.61	8.45	10.10	11.80	13.50	15.20	16.90	18.60	20.30	-	-	-	-	-	-	-	-
	30% GF*	2.93	3.90	4.88	5.85	6.83	7.80	8.78	9.75	11.70	13.70	15.60	-	-	-	-	-	-	-	-	-	-	-	-
	450FC30	2.84	3.77	4.72	5.67	6.62	7.56	8.51	9.46	11.32	13.26	15.10	-	-	-	-	-	-	-	-	-	-	-	-
POLYCARBONATE	Nat, Blk	2.34	3.12	3.90	4.68	5.46	6.24	7.02	7.80	9.36	10.90	12.50	14.10	15.60	17.20	18.70	20.30	21.90	23.40	25.00	-	-	-	-
	20% GF*	2.61	3.49	4.36	5.23	6.10	6.97	7.84	8.71	10.50	12.20	13.90	15.70	17.40	-	-	-	-	-	-	-	-	-	-
POLYSULFONE	Nat, Blk	2.42	3.23	4.03	4.84	5.64	6.45	7.26	8.06	9.68	11.30	12.90	14.50	16.10	17.70	19.40	21.00	22.60	24.20	25.80	-	-	-	-
PPO / NORYL®	Blk EN265	2.11	2.82	3.52	4.22	4.93	5.62	6.32	7.03	8.44	9.84	11.22	12.65	14.08	15.50	16.83	18.26	19.69	21.11	22.54	-	-	-	-
	GFN3*	2.52	3.36	4.19	5.03	5.87	6.71	7.55	8.39	10.10	11.70	13.40	15.10	16.80	18.50	20.10	-	-	-	-	-	-	-	-
PPS	Natural	-	3.52	4.39	5.27	6.15	7.03	7.91	8.78	10.60	12.30	14.10	-	-	-	-	-	-	-	-	-	-	-	-
	40% GF*	-	4.28	5.33	6.40	7.47	8.53	9.60	10.70	12.80	14.90	17.00	-	-	-	-	-	-	-	-	-	-	-	-
PVDF	Nat, Blk	-	4.63	5.78	6.94	8.10	9.26	10.42	11.60	13.90	16.20	18.50	20.80	23.20	25.50	27.80	30.10	32.40	34.70	37.00	39.35	41.67	44.00	46.30
RADEL®	Nat, Blk	2.84	3.37	4.21	5.06	5.90	6.74	7.59	8.43	10.11	11.83	13.46	15.20	16.83	18.56	20.20	21.93	23.56	25.30	26.93	-	-	-	-
ULTEM®	Nat, Blk	2.48	3.30	4.13	4.96	5.78	6.61	7.44	8.26	9.91	11.60	13.20	14.90	16.50	18.20	19.80	21.50	23.10	24.80	26.40	-	-	-	-

\* Supplied Unplaned

TOLERANCES	
THICKNESS	+0.025" -0.000"
WIDTH	+0.250" -0.000"
LENGTH	0.500" -0.000"

Delrin is a registered tradename of Dupont  
 PEEK is a registered trademark of Victrex  
 Noryl and Ultem are registered trademarks of General Electric  
 Radel is a registered trademark of Solvay Advanced Polymers, LLC  
 Halar is a registered trademark of Solvay Solexis, Inc